



4067-M-50 M/LS RESIN

4067-M-50 M/LS RESIN produces durable interior or exterior coatings, providing easy brushing, high gloss, and excellent weather resistance. It is suitable for air dry, force dry, or baked coatings.

SOLUTION PROPERTIES:

| | |
|--|------------------------|
| Non-volatile by weight | 50 ± 1.0% |
| Non-volatile by volume | 41 ± 1.0% |
| Weight per gallon @ 25°C | 7.60 ± 0.10 pounds |
| Viscosity @ 25°C | Y – Z ₁ |
| Reduced Viscosity @ 25°C (40% NV in Mineral Spirits) | G - J |
| Coplor (Gardner) | 10 maximum |
| Flash Point (SETA) | 104°F |
| Solvent | Exempt Mineral Spirits |

SOLID RESIN PROPERTIES:

| | |
|--------------------|--------------|
| Phthalic Anhydride | 30% |
| Oil Type | Mixed Drying |
| Oil Length | Medium |
| Acid Value | 12 maximum |

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

| | | | |
|------|---|-------|-----------|
| 0.01 | - | 0.03% | Cobalt |
| 0.15 | - | 0.30% | Zirconium |
| 0.01 | - | 0.04% | Calcium |

5/30/06

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232