



### **4495-100 L/T ISO RESIN**

**4495-100 L/T ISO RESIN** is an isophthalic modified resin made from tall oil fatty acids. 4495-100 may be used in place of linseed oil/bodied linseed oil in house paints or as a modifier for latex paints. Improvements in dry, yellowing, and durability will be seen when 4495-100 is used to place linseed oil.

#### **SOLUTION PROPERTIES:**

Non-volatile by weight	99 ± 1.0%
Weight per gallon @ 25°C	8.2 ± 0.10 pounds
Viscosity @ 25°C	Z <sub>2</sub> – Z <sub>4</sub>
Color, Gardner	10 maximum
Flash Point (Seta)	>200°F

#### **SOLID RESIN PROPERTIES:**

IPA Content	11%
Oil Type	TOFA
Oil Length	Long
Acid Value	8 maximum

7/22/98

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232