



4699-V-50 VT ALKYD COPOLYMER RESIN

4699-V-50 VINYL TOLUENE ALKYD COPOLYMER RESIN is supplied at 50% non-volatile in an exempt solvent system. It exhibits good toughness, hardness, gloss retention and water resistance. Recommended for use as fast dry enamels, aerosol paints, industrial primers and enamels, and clear wood sealers/finishes.

SOLUTION PROPERTIES:

| | |
|--|------------------------------------|
| Non-volatile by weight | 50 ± 1% |
| Non-volatile by volume | 41 ± 1% |
| Weight per gallon @ 25°C | 7.4 ± 0.10 Pounds |
| Viscosity @ 25°C | Y – Z ₁ |
| Reduced Viscosity @ 25°C (40% non-volatile exempt VM&P Naphtha) | N – Q |
| Color (Gardner) | 7 maximum |
| Solvent | Rule 66 VM&P/Mineral Spirits Blend |
| Flash Point (SETA) | 56°F |
| Appearance | Light yellow liquid |
| Dry Time @ 22°C: | |
| set-to-touch | 5-7 minutes |
| cotton free | 10-12 minutes |
| tack free | 25-30 minutes |

SOLID RESIN PROPERTIES:

| | |
|----------|---------|
| Oil Type | Linseed |
|----------|---------|

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

- 0.03% Cobalt
- 0.15% Calcium

2/3/98

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.