



4702-X-50 CHAIN STOPPED ALKYD RESIN

4702-X-50 CHAIN STOPPED ALKYD RESIN is based on low rosin, tall oil fatty acids. This resin gives rapid set and tack free times in air dry systems.

SOLUTION PROPERTIES:

Non-volatile by weight	50 ± 1%
Non-volatile by volume	42 ± 1%
Weight per gallon @ 25°C	8.25 ± 0.10 pounds
Viscosity @ 25°C	X – Z
Reduced Viscosity (40% N.V. in Xylene)	F – J
Color (Gardner)	6 maximum
Solvent	Xylene
Flash Point (Seta)	80°F

SOLID RESIN PROPERTIES:

Phthalic Anhydride	39%
Oil Type	TOFA
Oil Length	Short
Acid Value	12 maximum

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

0.03	-	0.06% Cobalt
0.2	-	0.3% Zirconium

3/27/96

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232