



4724-XT-80 HIGH SOLIDS VT ALKYD COPOLYMER RESIN

4724-XT-80 HIGH SOLIDS VINYL TOLUENE ALKYD COPOLYMER RESIN is supplied at 80% non-volatile in a blend of xylene and toluene. The resin exhibits rapid dry, good toughness, and hardness. It is intended for use in fast drying industrial finishes with low VOCs.

SOLUTION PROPERTIES:

Non-volatile by weight	80 ± 2%
Non-volatile by volume	76 ± 2%
Weight per gallon @ 25°C	8.75 ± 0.10 pounds
Viscosity @ 25°C	Z ₄ – Z ₆
Color (Gardner)	18 maximum
Flash Point (SETA)	68°F
Solvent	Xylene/Toluene
Dry Time @ 22°C (with recommended driers)	18 – 30 minutes

SOLID RESIN PROPERTIES:

Acid Value	8 maximum
Modifier	Vinyl Toluene
Oil Type	Mixed Drying

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

- 0.05% Cobalt
- 0.08% Calcium
- 0.12% Zirconium

2/22/06

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232