



4752-M-60 OIL MODIFIED URETHANE

4752-M-60 OIL MODIFIED URETHANE is a general purpose oil modified urethane supplied at 60% solids in Mineral Spirits. It is designed primarily for architectural finishes; however, it can be used for industrial topcoats as well. 4752-M-60 is particularly good for floor and exterior finishes.

SOLUTION PROPERTIES:

Non-volatile by weight	60 ± 1%
Non-volatile by volume	55 ± 1%
Weight per gallon @ 25°C	7.6 ± 0.1 pounds
Viscosity @ 25°C	Y – Z ₁
Reduced Viscosity @ 25°C	
40% non-volatile in Mineral Spirits	Less than A
50% non-volatile in Mineral Spirits	C – F
Color (Gardner)	6 max.
Flash Point (SETA)	108°F
Tack Free Time @ 25°C	3 – 4 Hours
Cure	Air Dry

SOLID RESIN PROPERTIES:

Oil Type	Linseed Oil
Oil Length	Medium to Long
Acid Value	2.0 max.

2/3/98

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232