



4772-V-60VT/OIL COPOLYMER RESIN

4772-V-60VT/OIL COPOLYMER RESIN is supplied at 60% non-volatile in VM&P Naphtha. The resin can be used in the manufacture of fast drying enamels, primers, aerosol paints, sanding sealers, and hammertone finishes. The products made with this resin dry primarily by evaporation of solvent from the surface of the coating giving a rapid dry.

SOLUTION PROPERTIES:

Non-volatile by weight	60 ± 1%
Non-volatile by volume	51 ± 1%
Weight per gallon @ 25°C	7.45 ± 0.1 pounds
Viscosity @ 25°C	Y – Z ₁
Reduced Viscosity @ 25°C (40% non-volatile in VM&P Naphtha)	B – E
Color (Gardner)	7 maximum
Flash Point (SETA)	52°F
Solvent	VM&P Naphtha

SOLID RESIN PROPERTIES:

Oil Type	Linseed
Modifier	Vinyl Toluene

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

0.02 - 0.04% Cobalt

6/5/98

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.
