



4906-EEP-85 SATURATED POLYESTER RESIN

4906-EEP-85 SATURATED POLYESTER RESIN is a high solids polyester resin with an excellent balance of cure response, adhesion, flexibility, and impact resistance.

SOLUTION PROPERTIES:

Non-volatile by weight	85 ± 1.0%
Non-volatile by volume	82 ± 1.0%
Weight per gallon @ 25°C	9.80 ± 0.1 pounds
Viscosity @ 25°C	Z ₃ – Z ₅
Flash Point (SETA)	136°F
Color, Gardner	3 maximum
Solvent(s)	EEP
Cure Type	Bake

SOLID RESIN PROPERTIES:

Phthalic Anhydride	Present
Oil Type	Oil Free
Oil Length	Not applicable
Acid Value	10 max.
Modifier	None
OHN	155

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

Not applicable

10/01/96

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232