



4911-T-80 HIGH SOLIDS MEDIUM OIL ALKYD

4911-T-80 HIGH SOLIDS MEDIUM OIL ALKYD is designed with a rapid set-to-touch and tack free time.

SOLUTION PROPERTIES:

Non-volatile by weight	80 ± 1%
Non-volatile by volume	76.5 ± 1%
Weight per gallon @ 25°C	8.56 ± 0.1 pounds
Viscosity @ 25°C	Z ₂ – Z ₄
Reduced Viscosity @ 25°C (70% in Toluene)	T – W
Flash Point (SETA)	45°F
Color (Gardner)	9 maximum
Solvent (Present)	Toluene
Cure Type	Air or Force Dry

SOLID RESIN PROPERTIES:

Phthalic Anhydride	Present
Oil Type	Mixed Fatty Acids
Oil Length	Medium
Acid Value	10 maximum
Modifier(s)	None
OHN	N/A

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

0.04	-	0.08%	Cobalt
0.04	-	0.08%	Calcium
0.1	-	0.4%	Zirconium

10/01/96

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.
