



4940-MKT-75 HIGH SOLIDS CHAIN STOPPED SHORT OIL ALKYD

4940-MKT-75 HIGH SOLIDS CHAIN STOPPED SHORT OIL ALKYD based on tall oil. It is recommended for high solids industrial enamels and primers. This resin has an extremely fast set time and rate of through dry.

SOLUTION PROPERTIES:

Non-volatile by weight	75 ± 1%
Non-volatile by volume	68 ± 1%
Weight per gallon @ 25°C	8.83 ± 0.1 pounds
Viscosity @ 25°C	Z – Z ₂
Reduced Viscosity @ 25°C (60% Toluene)	F – I
Flash Point (Seta)	45°F
Color (Gardner)	6 maximum
Solvent Present	MPK/Toluene
Cure Type	Air dry or force dry

SOLID RESIN PROPERTIES:

Phthalic Anhydride	Present
Oil Type	TOFA
Oil Length	Short
Acid Value	12 Maximum
Modifier	None
OH Equivalent Weight	N/A

DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):

0.20	-	0.40%	Zirconium
0.03	-	0.04%	Cobalt
0.01	-	0.02%	Manganese

9/18/06

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232