



4943-T-50 ACRYLIC RESIN SOLUTION

4943-T-50 ACRYLIC RESIN SOLUTION is a solution acrylic resin supplied at 50% non-volatile by weight in toluene. It is intended to be used in air dry or force dry industrial/OEM finishes. 4943-T-50 will give finishes with outstanding adhesion, toughness and weathering.

SOLUTION PROPERTIES:

Non-volatile by weight	50 ± 2%
Non-volatile by volume	45 ± 2%
Weight per gallon @ 25°C	7.9 ± 0.21 pounds
Viscosity @ 25°C	2000 – 4000 cps
Reduced Viscosity @ 25°C	not run
Flash Point (SETA)	45°F
Color (Gardner)	3 maximum
Solvent (Present)	Toluene
Cure Type	Air dry, force dry

SOLID RESIN PROPERTIES:

Phthalic Anhydride	Absent
Oil Type	None
Oil Length	Not applicable
Acid Value	Not applicable
Modifier	Not applicable
OHN	Not applicable

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

None recommended.

3/25/98

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232