



**4963-V-60 VT/OIL COPOLYMER RESIN**

**4963-V-60 VT/OIL COPOLYMER RESIN** is a quick drying VT/Oil Copolymer Resin cut to 62% non-volatile in VM&P Naphtha. Some of the suggested uses include quick drying OEM finishes, aerosol enamels and primers, toy enamels, and primers/sealers.

**SOLUTION PROPERTIES:**

Non-volatile by weight	62 ± 2%
Non-volatile by volume	53 ± 2%
Weight per Gallon @ 25°C	7.45 ± 0.1 pounds
Viscosity @ 25°C (Gardner)	T – W
Reduced Viscosity @ 25°C	Not determined
Flash Point (SETA)	50°F
Color, Gardner	8 maximum
Solvent	VM&P Naphtha
Cure Type	Air dry/force dry

**SOLID RESIN PROPERTIES:**

Phthalic Anhydride	None
Acid Value	8 maximum
Modifier	Vinyl Toluene
Oil Type	Linseed
Oil Length	Medium
OH Equivalent Weight	N/A

**DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):**

0.05	-	0.08% Cobalt
0.02	-	0.04% Manganese

8/17/99

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.