



## **4984-MBA-80 HIGH SOLIDS HAPS-FREE CHAIN STOPPED SHORT OIL**

**4984-MBA-80 HIGH SOLIDS HAPS-FREE CHAIN STOPPED SHORT OIL** can be used for air dry, force dry, and baking applications and is intended for industrial and OEM coatings.

### **SOLUTION PROPERTIES:**

Non-volatile by weight	80 ± 2%
Non-volatile by volume	76 ± 2%
Weight per gallon @ 25°C	8.9 ± 0.15 pounds
Viscosity @ 25°C	Z <sub>3</sub> – Z <sub>5</sub>
Flash Point (Seta)	Not run
Color (Gardner)	8 maximum
Solvent (s) Present	MBK/n-Butyl Acetate
Cure Type	Air dry/Force dry/Bake

### **SOLID RESIN PROPERTIES:**

Phthalic Anhydride	Present
Oil Type	Oxidizing
Oil Length	Short
Acid Value	12 maximum
Modifier	None
OH Equivalent Weight	N/A

### **DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):**

0.06	-	0.15%	Cobalt
0.08	-	0.18%	Calcium
0.05	-	0.10%	Zirconium

10/17/00

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232