



4987-V-60VT MODIFIED ALKYD RESIN

4987-V-60VT MODIFIED ALKYD RESIN is a fast drying vinyl toluene modified alkyd resin intended for use in fast drying primers and enamels. Its adhesion and flexibility are very good and it can be used on a variety of surfaces including wood and metal.

SOLUTION PROPERTIES:

Non-volatile by weight	60 ± 1%
Non-volatile by volume	53 ± 1%
Weight per gallon @ 25°C	7.47 ± 0.15 pounds
Viscosity @ 25°C	Z ₃ - Z ₅
Reduced Viscosity @ 25°C (40% VM&P)	E - H
Flash Point (SETA)	56°F
Color (Gardner)	8 maximum
Solvent Present	VM&P Naphtha
Cure Type	Air Dry, Force Dry

SOLID RESIN PROPERTIES:

Phthalic Anhydride	Present
Oil Type	Mixed Drying
Oil Length	Medium
Acid Value	10 max.
Modifier	Vinyl Toluene
OH Equivalent Weight	N/A

DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):

0.04	-	0.10% Cobalt
0.04	-	0.08% Zirconium

2/22/06

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232