



4990-X-75 HIGH SOLIDS ACRYLIC MODIFIED ALKYD

4990-X-75 HIGH SOLIDS ACRYLIC MODIFIED ALKYD RESIN is intended for industrial and maintenance finishes.

SOLUTION PROPERTIES:

Non-volatile by weight	75 ± 2%
Non-volatile by volume	69 ± 2%
Weight per gallon @ 25°C	8.55 ± 0.2 pounds
Viscosity @ 25°C	Z ₄ - Z ₆
Flash Point (SETA)	80°F
Color (Gardner)	8 maximum
Solvent Present	Xylene
Cure Type	Air Dry/Force Dry

SOLID RESIN PROPERTIES:

Phthalic Anhydride	Present
Oil Type	Mixed Drying
Oil Length	Medium
Acid Value	12 max.
Modifier	Acrylic
OH Equivalent Weight	N/A

DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):

0.05	-	0.10% Cobalt
0.05	-	0.10% Zirconium

2/11/02

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232