



5017-M-60 CHLORENDIC MODIFIED ALKYD RESIN

5017-M-60 CHLORENDIC MODIFIED ALKYD RESIN is formulated to impart improved fire retardency and decreased dry time.

SOLUTION PROPERTIES:

Non-volatile by weight	60 ± 1%
Non-volatile by volume	Not determined
Weight per gallon @ 25°C	8.26 ± 0.15 pounds
Viscosity @ 25°C	U-W
Flash Point (SETA)	104°F
Color (Gardner)	10 max.
Solvent(s) Present	Mineral Spirits
Cure Type	Air dry

SOLID RESIN PROPERTIES:

Phthalic Anhydride	None
Oil Type	TOFA
Oil Length	Medium
Acid Value	8 max.
Modifier(s)	Chlorendic Anhydride
OH Equivalent Weight	N/A

DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):

0.08% Cobalt
0.15% Zirconium

12/3/04

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232