



## **5022-M-60 OIL MODIFIED URETHANE RESIN**

**5022-M-60 OIL MODIFIED URETHANE RESIN** is a 60% non-volatile oil modified urethane resin intended for fast drying and abrasion resistant wood finishes. Uses include floor finishes, interior clears for wood and metal, maintenance finishes, aerosol finishes, and implement finishes.

### **SOLUTION PROPERTIES:**

Non-volatile by weight	60 ± 1%
Non-volatile by volume	53 ± 1%
Weight per gallon @ 25°C	7.50 ± 0.15 pounds
Viscosity @ 25°C	W – Y
Reduced Viscosity @ 25°C (50% MS)	D – G
Flash Point (SETA)	104°F
Color (Gardner)	5 maximum
Solvent Present	Mineral Spirits
Cure Type	Air Dry, Force Dry

### **SOLID RESIN PROPERTIES:**

Phthalic Anhydride	Absent
Oil Type	Mixed Drying
Oil Length	N/A
Acid Value	4 max.
Modifier	Urethane
OH Equivalent Weight	N/A

### **DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):**

0.03 - 0.06% Cobalt

2/22/06

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232