



5026-M-50 MEDIUM OIL ALKYD RESIN

5026-M-50 MEDIUM OIL ALKYD RESIN which is supplied at 50% non-volatile. It is intended for interior and exterior use.

SOLUTION PROPERTIES:

| | |
|--------------------------|---------------------------------|
| Non-volatile by weight | 50 ± 1% |
| Non-volatile by volume | 43 ± 1% |
| Weight per gallon @ 25°C | 7.58 ± 0.30 pounds |
| Viscosity @ 25°C | Z ₄ – Z ₅ |
| Flash Point (SETA) | 104°F |
| Color (Gardner) | 10 max. |
| Solvent(s) Present | Mineral Spirits |
| Cure Type | Air dry/force dry |

SOLID RESIN PROPERTIES:

| | |
|----------------------|---------|
| Phthalic Anhydride | Present |
| Oil Type | TOFA |
| Oil Length | Medium |
| Acid Value | 10 max. |
| Modifier(s) | None |
| OH Equivalent Weight | N.A. |

DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):

| | | | |
|------|---|-------|-----------|
| 0.03 | - | 0.05% | Cobalt |
| 0.20 | - | 0.40% | Zirconium |
| 0.03 | - | 0.05% | Calcium |

8/21/02

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.
