



5060-SP-70 WATER REDUCIBLE ALKYD RESIN

5060-SP-70 WATER REDUCIBLE ALKYD RESIN intended for use in air dry and force dry industrial finishes. It will give good corrosion and water resistance when properly formulated.

SOLUTION PROPERTIES:

Non-volatile by weight	70 ± 1%
Non-volatile by volume	65 ± 1%
Viscosity @ 25°C	Z ₄ – Z ₆
Weight per gallon @ 25°C	8.65 ± 0.1 pounds
Flash Point (Seta)	92°F
Color	8 maximum
Solvent	2-butanol/n-propoxypropanol

SOLID RESIN PROPERTIES:

Acid Value	37-43
Oil Type	Mixed Drying
Oil Length	Short

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

0.05	-	0.8% Cobalt
0.10	-	0.20% Zirconium

6/16/06

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232