



## **5064-M-55 OIL MODIFIED URETHANE**

**5064-M-55 OIL MODIFIED URETHANE** is a fast drying general purpose oil modified urethane supplied at 55% solids in Mineral Spirits. It is designed primarily for architectural finishes; however, it can be used for industrial topcoats as well. 5064-M-55 is particularly good for floor and exterior finishes.

### **SOLUTION PROPERTIES:**

Non-volatile by weight	55 ± 1%
Non-volatile by volume	50 ± 1%
Weight per gallon @ 25°C	7.6 ± 0.1 pounds
Viscosity @ 25°C	W - Y
Color (Gardner)	5 max.
Flash Point (SETA)	108°F
Tack Free Time @ 25°C	1 – 2 Hours
Cure	Air Dry

### **SOLID RESIN PROPERTIES:**

Oil Type	Soya Oil
Oil Length	Medium
Acid Value	3.0 max.

8/1/07

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---

ROUTE 993 ■ P. O. BOX 607 ■ MANOR, PA 15665 ■ (724) 864-8200 ■ FAX (724) 864-8232