



**5065-XV-60 PHENOLIC/ROSIN MODIFIED ALKYD RESIN**

**5065-XV-60 PHENOLIC/ROSIN MODIFIED ALKYD RESIN** is a short oil, phenolic and rosin modified alkyd resin supplied at 60% non-volatile by weight. It is a rapid setting resin for use in primers and fast drying industrial enamels.

**SOLUTION PROPERTIES:**

Non-volatile by weight	60 ± 1%
Non-volatile by volume	51 ± 1%
Weight per Gallon @ 25°C	8.1 ± 0.10 pounds
Viscosity @ 25°C	Z2- Z4
Reduced Viscosity (40% non-volatile)	G - J
Color (Gardner)	10 maximum
Solvent	Xylene/VM&P Naphtha
Flash Point (SETA)	61°F
Appearance	Clear amber liquid

**SOLID RESIN PROPERTIES:**

Phthalic Anhydride	Present
Oil Type	Linseed
Oil Length	Short
Acid Number	20 maximum
Modifiers	Phenolic Resin; Rosin

**DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):**

0.04	-	0.08% Cobalt
0.1	-	0.3% Zirconium

8/02/07

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---